

## 陶瓷纖維毯

### CERAMIC FIBER BLANKET

由噴吹或用絲工藝生產的陶瓷纖維棉，經針刺、熱定型、縱橫切、打卷等工序製成，溫度等級為1100-1430℃。

By ejection or silk fling process of ceramic fiber, after needle, heat setting, and cutting process, made into blanket, temperature grade is 1100-1430℃.

#### 產品特性 PROPERTY

- 熱傳導率低，隔熱性佳。  
Low thermal conductivity, excellent thermal insulation.
- 熱穩定性良好。  
Excellent thermal stability.
- 優異的抗熱衝擊性能。  
Excellent thermal shock resistance.
- 高溫下化學穩定性好。  
Superior stable chemical property at high temperature.
- 高溫下熱收縮率低。  
Low heat shrinkage at high temperature.
- 低熱容量。  
Low heat capacity.



#### 產品技術性能 TECHNICAL PROPERTY

產品名稱 Product Name	杜熱背襯毯	杜熱K1260毯	杜熱S毯	杜熱Z毯
顏色 Color	白色 White	白色 White	白色 White	白色 White
溫度等級 Temperature grade	1100℃	1260℃	1260℃	1430℃
建議使用溫度 Recommend the use of temperature	1000℃	1150℃	1176℃	1343℃
熔點 Melting point	1648℃	1760℃	1760℃	1760℃
纖維直徑 Fiber diameter	2-4µm (平均值)	2.5-3.5µm (平均值)	2.5-3.5µm (平均值)	3µm (平均值)